

**Title: Sound Absorption Test Results** 

**Product: 1" Envirocoustic Wood Wool - Micro Strand** 

Application: Ceiling or Wall


Testing Standard: ASTM C423-17 (Type A Mount)

Test Date: 6/25/2018

Why this test: This test evaluates a products efficiency of absorbing sound at multiple frequencies. The test simulates the product's acoustical performance with a direct-attach ceiling or wall installation.

Test Result Summary: NRC - 0.60; SAA - 0.56

NRC	SAA		
0.60	0.56		
Frequency	Absorption		
(Hz)	Coefficient		
80	0.09		
100	0.09		
125	0.07		
160	0.06		
200	0.12		
250	0.19		
315	0.19		
400	0.32		
500	0.40		
630	0.46		
800	0.58		
1000	0.74		
1250	0.86		
1600	0.96		
2000	1.03		
2500	0.89		
3150	0.77		
4000	0.81		
5000	0.62		



Test ID: ESP028637P-1

# ASI TEST RESULT DISCLAIMER

ASI makes every effort to ensure the accuracy and reliability of the information provided. Laboratory testing is conducted by independent testing organizations. ASI does not guarantee that field tests or independent tests will not vary.



Element Materials Technology 662 Cromwell Avenue St Paul, MN 55114-1720 USA P 651 645 3601 F 651 659 7348 T 888 786 7555 info.stpaul@element.com element.com

# SOUND ABSORPTION TESTING CONDUCTED ON a 1" Micro Strand Cementitious Wood Fiber Acoustic Board

ASI
Date: June 25, 2018

123 Columbia Court North
Author: John Wegscheider
Chaska, MN 55318
Report Number: ESP028637P-1



EAR Controlled Data: This document contains technical data whose export and re-export/retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval is required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

These commodities, Technology, or software were exported from the United States in accordance with the Export Administration Regulations. Diversion contrary to U.S. law is prohibited.

This project shall be governed exclusively by the General Terms and Conditions of Sale and Performance of Testing Services by Element Materials Technology. In no event shall Element Materials Technology be liable for any consequential, special or indirect loss or any damages above the cost of the work.

Ear Controlled Data

This Page Alone is not a complete report



# Noise Reduction Coefficient (ASTM C423)

# **INTRODUCTION:**

This report presents the results of acoustical testing of a 1" Micro Strand Cementitious Wood Fiber Acoustic Board. This testing was requested by Mr. Conor Cook of ASI and was conducted on June 20, 2018.

This report must not be reproduced except in full without the approval of Element Materials Technology. The test results contained in this report pertain only to the specific assemblies tested and not necessarily to all similar constructions.

The results stated in this report represent only the specific construction and acoustical conditions present at the time of the test. Measurements performed in accordance with this standard on nominally identical constructions and acoustical conditions may produce different results.

## **TEST RESULTS SUMMARY:**

Noise Reduction Coefficient (NRC) Test Type A Mount				Test Results		
Test#	Sample Identification	Weight (lbs)	Weight (psf)	NRC	SAA	
1	1" Micro Strand Cementitious Wood Fiber Acoustic Board	157.2	2.25	0.60	0.56	

Tabular and graphical presentations of the data are presented under "TEST RESULTS" below.

# **SPECIMEN DESCRIPTION:** (Also see "Test Results")

The Specimen was described as a 1" Micro Strand Cementitious Wood Fiber Acoustic Board. The overall sample size was 70.875" x 141.75" or 69.8 ft2. Nine (9) Panels were used and butted together. Each Panel measured 23.6875" x 47.25" and weighed 17.5 lbs.. The edges of the specimen were sealed with tape.

June 25, 2018

Ear Controlled Data



# **TEST PROCEDURE AND EQUIPMENT:**

# Sound Absorption Test

ASTM C 423-17," Sound Absorption and Sound Absorption Coefficient by the Reverberation Room Method", was followed in every respect. The samples were placed in a Type A mounting method in accordance with ASTM E795-16.

NRC was calculated by rounding the sound absorption coefficients for 250, 500, 1000 and 2000 Hz to the nearest 0.05. SAA was calculated by rounding the sound absorption coefficients for the twelve frequencies from 200 Hz to 2500 Hz to the nearest 0.01.

# **TEST EQUIPMENT:**

Acoustic Lab Calibrated Test Equipment For NRC Tests (Reverb Chamber Only)

Item Description	ID#	Manufacturer/Model	Serial #	Calibration Due
1/2" Pressure Condenser Microphone	PT-162-216	BSWA/MP253	450005	11/2/18
Microphone Calibrator	MM440-003	Bruel & Kjaer/4230	282266	11/2/18
Data Acquisition Module	PT-162-107	National Instruments/NI9234	1735986-1893EB3	6/6/19
Temp and Humidity Transmitter	PT-162-077	Dwyer Instruments/Series RH	M90714-E4SV-Y	5/31/19

June 25, 2018



# **Test Result:**

## SOUND ABSORPTION


ASTM C423


## General Information

Project No:	ESP028637P-1
Customer:	ASI
Test Date:	06-20-2018
Specimen ID:	1 Inch Micro Strand
Specimen Description:	Cementitious Wood Fiber Acoustic Board 1" x 23 11/16" x 47 1/4" Panel
Specimen Dimensions - Area:	70.87" W x 141.75" H - 69.77 ft²
Operator:	MJC

#### Data Table

	absorption empty (m²)	absorption * sample (m²)	Absorption Coefficient
80	3.79	0.61	0.09
100	4.84	0.56	0.09
125	3.81	0.45	0.07
160	3.49	0.37	0.06
200	3.98	0.81	0.12
250	4.08	1.24	0.19
315	3.96	1.24	0.19
400	4.02	2.00	0.31
500	4.37	2.58	0.40
630	4.65	2.98	0.46
800	5.11	3.78	0.58
1000	5.54	4.78	0.74
1250	5.88	5.60	0.86
1600	6.44	6.20	0.96
2000	7.20	6.70	1.03
2500	7.88	5.80	0.89
3150	8.98	4.99	0.77
4000	10.48	5.24	0.81
5000	13.27	3.99	0.62





**NRC** 0.60

SAA 0.56

\* based on an extended plane area of 69.77 ft<sup>2</sup>

John Wegscheider Manager, Product Validation 651-659-7353

Ear Controlled Data

Report Number ESP028637P-1